



Product Data Sheet



Ralston Aqua Wood & Parquet Lacquer

Ralston Colour & Coatings B.V.

Russenweg 14 - 8041 AL Zwolle
P.O. Box 205 - 8000 AE Zwolle
The Netherlands
T +31 38 429 11 00
F +31 38 421 04 14
E info@ralstoncolour.com
I www.ralstoncolour.com

Description

High-quality, non-dilutable, clear satin gloss varnish on the basis of a specific urethane technology.

Application

Interior, as an abrasion resistant finish of wood. Specifically for (parquet) floors, stairs, doors, furniture, boarding etc.

Principal characteristics

- odour free
- fast drying
- excellent scratch and abrasion resistance
- less environmental polluting

Colour and gloss

Colourless
Satin gloss

Technical data

At 20°C and 65% R.H.

Density:	approx. 1.1 kg/dm ³
Viscosity:	approx. 65 K.U.
Solids content:	approx. 31 volume %
Dust-dry:	approx. 0.5 - 1 hour
Recoatable:	approx. 4 hours
Accessible:	approx. 16 hours, hardened after a few days

Spreading rate and film thickness

Film thickness

35 microns dry (approx. 115 microns wet)

Theoretical spreading rate

At 35 microns dry: 8,6 m²/l

Practical spreading rate

Dependent on surface and application method 60-85% of the theoretical spreading rate



Product Data Sheet

Ralston Aqua Wood & Parquet Lacquer (continued)

Application conditions

- Ambient temperature: min. 7°C
- Relative humidity: max. 85%

Instructions for use

- Stir well before use
- Dilution: ready to use (max. 5% water if desired)
- Clean tools with water

Product details

- Package: 1 and 2.5 liter
- Storage: in unopened, original package at a cool, dry and frost-proof area
- Maximum usage period: 12 months

Environment and health

- Flash point: none
- Safety regulations: National legislation regarding safety, health and environment applies to users. For more information and current data, see the latest version of the Material Safety Data Sheet.