



## Product Data Sheet



# Ralston Uni-Acryl Satin

### Ralston Colour & Coatings B.V.

Russenweg 14 - 8041 AL Zwolle  
P.O. Box 205 - 8000 AE Zwolle  
The Netherlands  
T +31 38 429 11 00  
F +31 38 421 04 14  
E [info@ralstoncolour.com](mailto:info@ralstoncolour.com)  
I [www.ralstoncolour.com](http://www.ralstoncolour.com)

### Description

Water-dilutable satin gloss enamel on the basis of acrylate dispersion.

### Application

On - according to valid prescriptions - pretreated wood, concrete, metal, plaster, pvc, wooden and stony sheet work, exterior and interior. Very well suitable to be applied on existing paintwork (after cleaning and sanding).

### Principal characteristics

- fast drying
- high elasticity and moisture regulation
- good durability
- less environmental polluting

### Principal characteristics

All colours available through the Ralston AQ tinting system  
Satin gloss

### Technical data

#### At 20°C and 65% R.H.

Density:	approx. 1.2 kg/dm <sup>3</sup>
Viscosity:	approx. 95 K.U.
Solids content:	approx. 40 volume %
Dust-dry:	approx. 0.5-1 hour
Recoatible:	approx. 4 hours

### Spreading rate and film thickness

#### Film thickness

35 microns dry (approx. 80 microns wet)

#### Theoretical spreading rate

At 35 microns dry: 11.4 m<sup>2</sup>/l

#### Practical spreading rate

Dependent on surface and application method 60- 85% of the theoretical spreading rate.



## Product Data Sheet

### Ralston Uni-Acryl Satin (continued)

#### Application conditions

- Ambient temperature: min. 10°C
- Surface temperature: min. 3°C above dew point
- Relative humidity: max. 85%

#### Instructions for use

- Stir well before use
- Dilution: ready to use (max. 5% water if desired)
- Clean tools with water

#### Product details

- Package: 1 and 2.5 liter – BW and BTR  
Storage: in unopened, original package at a cool, dry and frost-proof area  
Maximum usage period: 12 months

#### Environment and health

- Flash point: none  
Safety regulations: National legislation regarding safety, health and environment applies to users.  
For more information and current data, see the latest version of the Material Safety Data Sheet.

N.B.: Characteristics and technical data are dependent on the colour. Values mentioned are averages.

- BW = Base White  
BTR = Base Transparent  
W = White

