



# Ralston Endurance

Exterior paints with extraordinary performance

- Ralston Endurance High Gloss
- Ralston Endurance Satin
- Ralston Endurance Primer



• paint • passion • people

**Ralston**  
COLOUR & COATINGS

# Endurance High Gloss, Satin & Primer

As a craftsman you go for the best painting. With the Ralston Endurance exterior paints you can deliver outstanding performance in all conditions. An Endurance paint system offers the ultimate power of protection and long-term protection of your real estate.



Exterior

## Ralston Endurance High Gloss

- Extremely long life span
- Fast initial drying
- Very high initial gloss & long gloss retention
- Excellent application properties

### Intended Use

As finishing coat on pre-treated wood, metal and plastic.



Exterior

## Ralston Endurance Satin

- Excellent outdoor durability
- Good gloss retention
- Excellent flow characteristics
- Can be applied year-round

### Intended Use

As finishing coat on pre-treated wood, metal and plastic.



Exterior

## Ralston Endurance Primer

- For optimum gloss performance
- Neat and smooth surface
- High filling
- Good (edge) coverage

### Intended Use

As wood primer, and as undercoat on pre-treated wood, metal and plastic.

	Ralston Endurance High Gloss	Ralston Endurance Satin
Theoretical Coverage *	13 m <sup>2</sup> /l	14,2 m <sup>2</sup> /l
Drying Time Condition	20 °C / 65 % R.H.	20 °C / 65 % R.H.
Dust-Free Drying Time **	2	2,5
Tack-Free Time **	3	4
Time To Recoat **	16	18
Wet Film Thickness	77 Mμ	70 Mμ
Dry Film Thickness	50 Mμ	45 Mμ
Gloss Level	High gloss, approx. 85 G.U. at 60 °	Satin gloss, approx. 30 G.U. at 60 °

	Ralston Endurance Primer
Theoretical Coverage *	16 m <sup>2</sup> /l
Drying Time Condition	20 °C / 65 % R.H.
Dust-Free Drying Time **	1,5
Tack-Free Time **	3
Time To Recoat **	16
Wet Film Thickness	63 Mμ
Dry Film Thickness	40 Mμ
Gloss Level	Satin gloss, approx. 20 G.U. at 60 °

\* Depends on application method, applied wet film thickness and surface

\*\* Drying time in hours

For more information visit [www.ralstoncolour.com](http://www.ralstoncolour.com)

Part of  
Royal Van Wijhe Verf

**Ralston**  
COLOUR & COATINGS

Ralston Colour & Coatings B.V.  
Postbus 205, 8000 AE Zwolle  
Nederland

+31(0)38 - 429 11 00  
[info@ralstoncolour.com](mailto:info@ralstoncolour.com)  
[www.ralstoncolour.com](http://www.ralstoncolour.com)

2023-06