



Scratch-resistant, satin gloss, anticorrosive pre-coat and finishing enamel based on urethane/alkyd resin.

- Scratch and abrasion resistant
- Anti-corrosive
- Good outdoor durability
- Excellent flow
- Easy in applying
- Low propensity to run and good (edge) coverage
- Hardly yellowing

www: Ralston Industrial Satin

## Application

Situation

Exterior, interior

Application

Exterior and interior, as a pre-coat and finishing enamel on pre-treated metal.

## Colors

Colours

All colours available via the Ralston ALK colour mixing system.

## Performance and features

Binder

Urethane alkyd resin

Pigment

High quality pigments

Density at 20°C

Approx. 1.22 kg/dm<sup>3</sup>

Viscosity at 20°C

Approx. 97 K.U.

Solids content

Approx. 46 volume %

Drying time (20°C / 65% R.H.)

Dust-free after approx. 2.5 hr, tack-free approx. 3.5 hr, recoatable approx. 16 hr.

Drying times are average values and provided as an indication only; actual drying time will depend on weather conditions, film thickness and choice of colour. Darker colours, applied in lower temperatures will take longer to dry than whites and lighter colours.

Elasticity

7 mm

Gloss level

Satin gloss, approx. 35 G.U. at 60°

Heat resistance

At dry load maximum 90°C.

NOTE: The properties and specifications can vary depending on the colour. The values stated are typical.

## Processing

Spray data air-assisted airless - pressure

14 - 16 MPa (140 - 160 bar), air support approx. 0,2 MPa (approx. 2 bar)

Spray data air-assisted airless - orifice

0,23 - 0,33 mm

Spray data air-assisted airless - dilution

0 - 5% naphtha

Spray data air spray - pressure

0,3 - 0,4 MPa (3 - 4 bar)

|                                |                                                                                                                                                                                                                                                                     |
|--------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Dilution                       | Ready to use. If necessary, dilute sparingly with white spirit or naphtha.                                                                                                                                                                                          |
| Tools/equipment cleaning       | White spirit or naphtha.                                                                                                                                                                                                                                            |
| Application temperature / R.H. | Min. 5 ambient and substrate temp., relative humidity max. 85%. Substrate temperature min. 3°C above dew point.                                                                                                                                                     |
| Theoretical coverage           | 13.2 m <sup>2</sup> /l                                                                                                                                                                                                                                              |
| Practical coverage             | Depending on the application method and the substrate, 60 - 85% of the theoretical coverage.                                                                                                                                                                        |
| Film thickness                 | 35 microns dry film thickness = approx. 76 microns wet film thickness                                                                                                                                                                                               |
| Mixing                         | Stir thoroughly before use.<br><br>Check the dew point regularly when applying at low temperatures. With wood and metal substrates, this can have a major influence on the ability to apply the coating, as well as on the drying and gloss of the applied coating. |

## Maintenance

|                      |                                                                                                                                                                                                                                                                                |
|----------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Maintenance interval | Approx. 5 - 6 years<br><br>Depending on location/ situation, surface to be treated, construction system, applied paint system and colour, mechanical impacting, etc.. The annual cleaning and touching up of damage prolongs the condition of the substrate and the paintwork. |
|----------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

## Environment and Health

|                        |                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                             |
|------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Flash point (°C)       | 35–40                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                       |
| Safety instructions    | The user is subject to the national legislation regarding safety, health and environment. For more information and current data, see the latest version of the Safety Data Sheet.                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                           |
| EU limit value VOC     | EU limit value for this product A/i: 500 g/l 2010. This product contains a maximum of 500 g/l VOCs.                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                         |
| BREEAM                 | We herewith conform that our product can be used in compliance with BREEAM International New Construction. As per HEA 9, required evidence – completion phase: C 1.1 through to 1.8; in evidence of compliance, the following must be submitted: 1. VOS Volatile Organic Substance content as determined by product recipe. 2. Products grouped by category in accordance with European Decopaint Directive 2004/42/EC – Enclosure 2: Emission norm for paints, lacquers and clear finishes, phase 2. 3. EU limit value for this product A/i: 500 g/l 2010. This product contains a maximum of 500 g/l VOCs. We apply the above harmonization procedure as recommended by the Dutch Green Building Council. |
| Belgian emission label | The product complies with the limit values and other stipulations of the Royal Decree of 8 May 2014, which defines the threshold levels for emissions to the internal environment from construction products for designated, specific uses, as published in the Belgian Government Gazette of 8 August 2014.                                                                                                                                                                                                                                                                                                                                                                                                |
| French emission label  | A+                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          |

## Item details

|           |                                                                                            |
|-----------|--------------------------------------------------------------------------------------------|
| Packaging | 1L, 2.5L                                                                                   |
| Storage   | Cool and above freezing point; do not allow product quality to deteriorate during storage. |

Use within

Use within 24 months of the date charge no. stated on the pack figures 1 and 2 = year, figures 3 and 4 = month, 5 and 6 = day of the month. Assumes unopened product.

# Ralston Industrial Satin

## System structure

### **New, exterior, untreated, non-ferrous metal (galvanised steel, aluminium, copper)**

- remove all traces of oxidation thoroughly, clean / degrease and sand
- prime with Ralston Uni-Primer
- pre-finish with Ralston Industrial Satin
- finish with Ralston Industrial Satin

### **New, exterior, untreated, exterior, ferrous metal (steel and iron)**

- remove all traces of rust, clean / degrease and sand
- apply 2 coats of primer Ralston Uni-Primer
- pre-finish with Ralston Industrial Satin
- finish with Ralston Industrial Satin

### **New, interior, untreated, non-ferrous metal (galvanised steel, aluminium, copper)**

- remove all traces of oxidation thoroughly, clean / degrease and sand
- prime with Ralston Uni-Primer
- pre-finish with Ralston Industrial Satin
- finish with Ralston Industrial Satin

### **New, interior, untreated, ferrous metal (steel and iron)**

- remove all traces of rust, clean / degrease and sand
- prime with Ralston Uni-Primer
- pre-finish with Ralston Industrial Satin
- finish with Ralston Industrial Satin

### **Existing, exterior, treated, non-ferrous metal (galvanised steel, aluminium, copper)**

- remove unsound paint coats
- remove all traces of oxidation thoroughly, clean / degrease and sand
- prime bare patches with Ralston Uni-Primer
- pre-finish patches or entire surface with Ralston Industrial Satin
- finish with Ralston Industrial Satin

### **Existing, exterior, treated, exterior, ferrous metal (steel and iron)**

- remove unsound paint coats
- remove all traces of rust, clean / degrease and sand
- prime bare patches 2x with Ralston Uni-Primer
- pre-finish patches or entire surface with Ralston Industrial Satin
- finish with Ralston Industrial Satin

### **Existing, interior, treated, non-ferrous metal (galvanised steel, aluminium, copper)**

- remove unsound paint coats
- remove all traces of oxidation thoroughly, clean / degrease and sand
- prime bare patches with Ralston Uni-Primer
- pre-finish patches or entire surface with Ralston Industrial Satin
- finish with Ralston Industrial Satin

### **Existing, exterior, treated, exterior, ferrous metal (steel and iron)**

- remove unsound paint coats
- remove all traces of rust, clean / degrease and sand
- prime bare patches with Ralston Uni-Primer
- pre-finish patches or entire surface with Ralston Industrial Satin
- finish with Ralston Industrial Satin

# Ralston Industrial Satin

## General remarks on paint systems and preparation

These remarks on paint application and maintenance are only general. The appropriate paint system to be applied will depend on both the substrate and the requirements to be met by the paintwork.

## Regularly clean and repair any damage to paintwork

Regularly (preferably annually), clean the paintwork and repair any physical or other damage to the substrate or paintwork. This will have a beneficial effect on the condition of the painted object and its paint coating.

## Adhesion between paint layers

Always sand or de-gloss between paint coating layers. This is essential for good adhesion of each new layer to the previous layer (with the exception of wall paints).

## Regularly check the dew point

When working in lower temperatures, check the dew point frequently. Never apply new paint/coating onto a substrate with condensation (dew). If you do so, the adhesion and film formation will be degraded. Moisture also causes poor drying, and can ruin the gloss.

## Repairs and compatibility with paint

Repairs to substrates, paintwork, connection joints/seams and glazing systems must be carried out with the appropriate products in accordance with the manufacturer's instructions. For wood repair, we prefer wood repair products based on epoxy or polyurethane and for sealing glazing joints to the Soudal Glaskit TS. The Soudal Acryrub CF2 can be used to seal joints and seams in interior wall paintwork. Prior to the commencement of the painting work, assess the mutual tolerance of the products to be applied.

## For treatment, metal substrates

Remove rust and zinc salts thoroughly, so that an oxidation-free surface is obtained. Immediately after de-rusting / sanding, degrease and apply a primer layer. Degrease new hot-dip galvanised steel and aluminium before applying a primer coat and then blast lightly with a fine non-metallic abrasive using appropriate pressure.

## NF DTU 59.1

The substrates must comply with the relevant DTU standards, particularly NF DTU 59.1. Prior assessment is necessary to determine the most suitable preparation based on their condition and nature (cleaning, washing/rinsing, sanding, scraping, degreasing, dulling, dusting...).

**Ralston Colour & Coatings B.V.**  
Part of Royal Van Wijk Verf

Russenweg 14  
P.O. Box 205  
8000 AE Zwolle  
Netherlands

T +31(0)38 - 429 11 00  
F +31(0)38 - 421 04 14  
E [info@ralstoncolour.com](mailto:info@ralstoncolour.com)  
W [www.ralstoncolour.com](http://www.ralstoncolour.com)

CoC Nr.  
05063230