



High quality, water-dilutable mat coating based on acrylate technology.

- Scratch and impact-resistant
- Long 'open time' and short recoatable time
- Neat, mat appearance
- Non yellowing
- Excellent flow and optimal hiding power
- Easy application
- VOC-low and little odour
- Resistant to skin oils from handling

www: Ralston Aqua Matt

## Application

Situation

Application

Interior

Interior, on pre-treated wood, metal, synthetics (hard pvc) and stony surfaces. Can be applied over the existing paintwork after first thoroughly cleaning and sanding the surface.

## Colors

Colours

White, other colours available through the Ralston AQ colour mixing system.

White, other colours available through the Ralston UNI Plus colour mixing system.

## Performance and features

Binder

Pigment

Density at 20°C

Viscosity at 20°C

Solids content

Drying time (20°C / 65% R.H.)

Acrylate technology

High quality pigments

Approx. 1.16 kg/dm<sup>3</sup>

Approx. 118 K.U.

Approx. 35 volume %

Dust-free after approx. 1 hr, recoatable after approx. 4 hr.

The stated drying times are typical and depend on such factors as temperature, humidity and the colour used. At low temperatures, darker colours have longer drying times than white and light colours.

Elasticity

Gloss level

7 mm

Matt, approx. 7 G.U. at 60°

NOTE: The properties and specifications can vary depending on the colour. The values stated are typical.

## Processing

Dilution

Tools/equipment cleaning

Ready to use. If necessary max. 5% water.

Water.

|                                |                                                                                                                                                                                                                                                                     |
|--------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Application temperature / R.H. | Min. 7 ambient and substrate temp., relative humidity max. 85%. Substrate temperature min. 3°C above dew point.                                                                                                                                                     |
| Theoretical coverage           | 10 m <sup>2</sup> /l                                                                                                                                                                                                                                                |
| Practical coverage             | Depending on the application method and the substrate, 60 - 85% of the theoretical coverage.                                                                                                                                                                        |
| Film thickness                 | 35 microns dry film thickness = approx. 100 microns wet film thickness                                                                                                                                                                                              |
| Mixing                         | Stir thoroughly before use.<br><br>Check the dew point regularly when applying at low temperatures. With wood and metal substrates, this can have a major influence on the ability to apply the coating, as well as on the drying and gloss of the applied coating. |

## Environment and Health

|                        |                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                             |
|------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Flash point (°C)       | Not applicable.                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                             |
| Safety instructions    | The user is subject to the national legislation regarding safety, health and environment. For more information and current data, see the latest version of the Safety Data Sheet.                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                           |
| EU limit value VOC     | EU limit value for this product A/d: 130 g/l 2010. This product contains a maximum of 130 g/l VOCs.                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                         |
| BREEAM                 | We herewith conform that our product can be used in compliance with BREEAM International New Construction. As per HEA 9, required evidence – completion phase: C 1.1 through to 1.8; in evidence of compliance, the following must be submitted: 1. VOS Volatile Organic Substance content as determined by product recipe. 2. Products grouped by category in accordance with European Decopaint Directive 2004/42/EC – Enclosure 2: Emission norm for paints, lacquers and clear finishes, phase 2. 3. EU limit value for this product A/d: 130 g/l 2010. This product contains a maximum of 130 g/l VOCs. We apply the above harmonization procedure as recommended by the Dutch Green Building Council. |
| Belgian emission label | The product complies with the limit values and other stipulations of the Royal Decree of 8 May 2014, which defines the threshold levels for emissions to the internal environment from construction products for designated, specific uses, as published in the Belgian Government Gazette of 8 August 2014.                                                                                                                                                                                                                                                                                                                                                                                                |
| French emission label  | A                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                           |

## Item details

|            |                                                                                                                                                                                                                                         |
|------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Packaging  | 0.5L, 1L, 2.5L, 5L                                                                                                                                                                                                                      |
| Storage    | Cool and above freezing point; do not allow product quality to deteriorate during storage.                                                                                                                                              |
| Use within | 12 Months in unopened packaging. After opening the packaging, the effect of 'preservatives' in the paint may be reduced. In exceptional cases, this can give bacteria and moulds free rein from outside, which could spoil the product. |

# Ralston Aqua Matt

## System structure

### New, interior, untreated, wood

- clean / degrease and sand
- prime with Ralston Aqua All-Primer BIOseries
- pre-finish with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua Matt

### New, interior, untreated, ferrous metal (steel and iron)

- remove all traces of rust, clean / degrease and sand
- prime with Ralston Uni-Primer
- pre-finish with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua Matt

### New, interior, untreated, non-ferrous metal (galvanised steel, aluminium, copper)

- remove all traces of oxidation thoroughly, clean / degrease and sand
- prime with Ralston Aqua All-Primer BIOseries
- pre-finish with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua Matt

### New, interior, untreated, plastics (hard PVC)

- clean / degrease thoroughly, and sand
- prime with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua Matt

### Existing, interior, treated, wood

- remove unsound paint coats
- clean / degrease and sand / rub down gloss thoroughly
- prime bare patches with Ralston Aqua All-Primer BIOseries
- pre-finish patches or entire surface with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua Matt

### Existing, interior, treated, non-ferrous metal (galvanised steel, aluminium, copper)

- remove unsound paint coats
- remove all traces of oxidation thoroughly, clean / degrease and sand
- prime bare patches with Ralston Aqua All-Primer BIOseries
- pre-finish patches or entire surface with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua Matt

### Existing, exterior, treated, exterior, ferrous metal (steel and iron)

- remove unsound paint coats
- remove all traces of rust, clean / degrease and sand
- prime bare patches with Ralston Uni-Primer
- pre-finish patches or entire surface with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua Matt

### Existing, interior, treated, plastics (hard PVC)

- remove unsound paint coats
- clean / degrease thoroughly, and sand
- prime/ pre-finish partially or entirely with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua Matt

# Ralston Aqua Matt

## General remarks on paint systems and preparation

These remarks on paint application and maintenance are only general. The appropriate paint system to be applied will depend on both the substrate and the requirements to be met by the paintwork.

## Adhesion between paint layers

Always sand or de-gloss between paint coating layers. This is essential for good adhesion of each new layer to the previous layer (with the exception of wall paints).

## Repairs and compatibility with paint

Repairs to substrates, paintwork, connection joints/seams and glazing systems must be carried out with the appropriate products in accordance with the manufacturer's instructions. For wood repair, we prefer wood repair products based on epoxy or polyurethane and for sealing glazing joints to the Soudal Glaskit TS. The Soudal Acryrub CF2 can be used to seal joints and seams in interior wall paintwork. Prior to the commencement of the painting work, assess the mutual tolerance of the products to be applied.

## Pretreatment, wooden substrates

Remove dirt and any weathered and/or degraded parts from wood and wood-based panels prior to application of the paint system in order to obtain a clean and sound substrate. By rounding off sharp edges, a longer protection of the substrate is obtained. Wood may contain up to 18% moisture during treatment.

## For treatment, metal substrates

Remove rust and zinc salts thoroughly, so that an oxidation-free surface is obtained. Immediately after de-rusting / sanding, degrease and apply a primer layer. Degrease new hot-dip galvanised steel and aluminium before applying a primer coat and then blast lightly with a fine non-metallic abrasive using appropriate pressure.

## Painting of synthetic substrates

There is no suitable paint system for synthetic materials such as PE and PP.

**NF DTU 59.1**

The substrates must comply with the relevant DTU standards, particularly NF DTU 59.1. Prior assessment is necessary to determine the most suitable preparation based on their condition and nature (cleaning, washing/rinsing, sanding, scraping, degreasing, dulling, dusting...).

**Ralston Colour & Coatings B.V.**  
Part of Royal Van Wijk Verf

Russenweg 14  
P.O. Box 205  
8000 AE Zwolle  
Netherlands

T +31(0)38 - 429 11 00  
F +31(0)38 - 421 04 14  
E [info@ralstoncolour.com](mailto:info@ralstoncolour.com)  
W [www.ralstoncolour.com](http://www.ralstoncolour.com)

CoC Nr.  
05063230