



- Ralston Aqua 3-in-1 Satin
- Ralston Aqua 2-in-1 Spray Satin

• paint • passion • people

Ralston
COLOUR & COATINGS



Exterior

Ralston Aqua 3-in-1 Satin

Intended Use

As a finish for wooden façade frames, window frames, doors, wood panelling etc.. Can also be applied over existing paint after thoroughly cleaning and sanding the surface.



Interior

Ralston Aqua 2-in-1 Spray Satin

Intended Use

As interior primer and top coat on wood and prepared metal and plastic.

Ralston Aqua 3-in-1 Satin

Theoretical Coverage *	12 m ² /l
Drying Time Condition	20 °C / 65 % R.H.
Dust-Free Drying Time **	0,5 - 1
Time To Recoat **	4
Wet Film Thickness	83 Mμ
Dry Film Thickness	35 Mμ
Gloss Level	Satin gloss, approx. 35 G.U. at 60 °

Ralston Aqua 2-in-1 Spray Satin

Theoretical Coverage *	6,3 m ² /l
Drying Time Condition	20 °C / 65 % R.H.
Dust-Free Drying Time **	0,75
Time To Recoat **	4
Wet Film Thickness	162 Mμ
Dry Film Thickness	60 Mμ
Gloss Level	Mild satin gloss, approx. 25 G.U. at 60 °

Part of
Royal Van Wijhe Verf

Ralston
COLOUR & COATINGS

Ralston Colour & Coatings B.V.
Postbus 205, 8000 AE Zwolle
Nederland

+31(0)38 - 429 11 00
info@ralstoncolour.com
www.ralstoncolour.com

2020-01