



Universal 4-season primer /undercoat with excellent filling and weather resistance, based on alkyd resin.

- Can be applied year-round '4 seasons'
- Easy to sand
- Moisture regulation
- Good flow characteristics and good filling power
- Good adhesion
- Easy in applying
- Does not require immediate overcoating, but can be overcoated at a later stage (\pm 2 years if 2 coats have been applied)

[productpage Ralston 4S Wood-Primer](#)

Intended use

Exterior
Interior
Exterior and interior, as wood primer, and as undercoat on pre-treated wood, metal and plastic.

Colors

Colours All colours available via the Ralston ALK colour mixing system.

Performance and features

Binder	Alkyd resin
Pigment	High quality pigments and fillers
Density at 20°C (kg/dm ³), approx.	1.3
Viscosity at 20°C (K.U.) , approx.	95
Solids content (volume %) , approx.	63
Drying time (20°C / 65% R.H.)	Dust-free after approx. 1 hr, tack-free approx. 3 hr, recoatable approx. 16 hr.
Drying time (5°C / 90% R.H.)	Dust-free after approx. 2 hr, tack-free approx. 5 hr, recoatable approx. 24 hr.
	Drying times are average values and provided as an indication only actual drying time will depend on weather conditions, film thickness and choice of colour. Darker colours, applied in lower temperatures will take longer to dry than whites and lighter colours.
Elasticity (mm)	6
Gloss level	Satin gloss, approx. 20 G.U. at 60°

NOTE: The properties and specifications can vary depending on the colour. The values stated are typical.

Processing

Product Data Sheet

Ralston 4S Wood-Primer

Application tool	brush roller air spray
Dilution	Ready to use. If necessary, dilute sparingly with white spirit or naphtha.
Tools/equipment cleaning	White spirit or naphtha.
Application temperature / R.H.	Min. 0 ambient and substrate temp., relative humidity max. 90. Substrate temperature min. 3°C above dew point.
Theoretical coverage (m ² /l)	14
Practical coverage	Depending on the application method and the substrate, 60 - 85% of the theoretical coverage.
Film thickness	45 microns dry film thickness = approx. 72 microns wet film thickness
Mixing	Stir thoroughly before use. Check the dew point regularly when applying at low temperatures. With wood and metal substrates, this can have a major influence on the ability to apply the coating, as well as on the drying and gloss of the applied coating.

Maintenance

Maintenance interval (years)	Approx. 2 (with a two-layer system)
------------------------------	-------------------------------------

Environment and Health

Flash point (°C)	41-52
Safety instructions	The user is subject to the national legislation regarding safety, health and environment. For more information and current data, see the latest version of the Safety Data Sheet.
EU limit value VOC	EU limit value for this product A/d: 300 g/l 2010. This product contains a maximum of 300 g/l VOCs.
BREEAM	We herewith conform that our product can be used in compliance with BREEAM International New Construction. As per HEA 9, required evidence – completion phase: C 1.1 through to 1.8 in evidence of compliance, the following must be submitted: 1. VOS Volatile Organic Substance content as determined by product recipe. 2. Products grouped by category in accordance with European Decopaint Directive 2004/42/EC – Enclosure 2: Emission norm for paints, lacquers and clear finishes, phase 2. 3. EU limit value for this product A/d: 300 g/l 2010. This product contains a maximum of 300 g/l VOCs. We apply the above harmonization procedure as recommended by the Dutch Green Building Council.
Belgian emission label	The product complies with the limit values and other stipulations of the Royal Decree of 8 May 2014, which defines the threshold levels for emissions to the internal environment from construction products for designated, specific uses, as published in the Belgian Government Gazette of 8 August 2014.
French emission label	A+

Item details

Packaging (l)	1, 2.5
Storage	Cool and above freezing point do not allow product quality to deteriorate during storage.
Use within	Use within 24 months of the date charge no. stated on the pack figures 1 and 2 = year, figures 3 and 4 = month, 5 and 6 = day of the month. Assumes unopened product.

Product Data Sheet
Ralston 4S Wood-Primer



System composition - advices

New, exterior, untreated, wood

- clean / degrease and sand
- prime with Ralston 4S Wood-Primer
- pre-finish with Ralston 4S Wood-Primer
- finish with Ralston Red label paints

New, exterior, untreated, wood

- clean / degrease and sand
- prime with Ralston 4S Wood-Primer
- pre-finish with Ralston 4S Wood-Primer
- finish with Ralston Red label paints

Existing, exterior, treated, wood

- remove unsound paint coats
- clean / degrease and sand / rub down gloss thoroughly
- prime bare patches with Ralston 4S Wood-Primer
- pre-finish patches or entire surface with Ralston 4S Wood-Primer
- finish with Ralston Red label paints

Existing, exterior, treated, wood

- remove unsound paint coats
- clean / degrease and sand / rub down gloss thoroughly
- prime bare patches with Ralston 4S Wood-Primer
- pre-finish patches or entire surface with Ralston 4S Wood-Primer
- finish with Ralston Red label paints

General remarks on paint systems and preparation

These remarks on paint application and maintenance are only general. The appropriate paint system to be applied will depend on both the substrate and the requirements to be met by the paintwork.

Regularly clean and repair any damage to paintwork

Regularly (preferably annually), clean the paintwork and repair any physical or other damage to the substrate or paintwork. This will have a beneficial effect on the condition of the painted object and its paint coating.

Adhesion between paint layers

Always sand or de-gloss between paint coating layers. This is essential for good adhesion of each new layer to the previous layer (with the exception of wall paints).

Regularly check the dew point

When working in lower temperatures, check the dew point frequently. Never apply new paint/coating onto a substrate with condensation (dew). If you do so, the adhesion and film formation will be degraded. Moisture also causes poor drying, and can ruin the gloss.

Repairs and compatibility with paint

Repairs to substrates, paintwork, connection joints/seams and glazing systems must be carried out with the appropriate products in accordance with the manufacturer's instructions. For wood repair, we prefer wood repair products based on epoxy or polyurethane and for sealing glazing joints to the Soudal Glaskit TS. The Soudal Acryrub CF2 can be used to seal joints and seams in interior wall paintwork. Prior to the commencement of the painting work, assess the mutual tolerance of the products to be applied.

Pretreatment, wooden substrates

Remove dirt and any weathered and/or degraded parts from wood and wood-based panels prior to application of the paint system in order to obtain a clean and sound substrate. By rounding off sharp edges, a longer protection of the substrate is obtained. Wood may contain up to 18% moisture during treatment.

The details in this product data sheet are correct at the time of printing. The information provided about this product is regularly updated, and amendments may therefore be made at any time without notice. Ralston Colour & Coatings B.V. expressly disclaims any and all liability related to damages resulting from errors or omissions in the information provided herein, except in the event of malicious intent or gross negligence.

Product Data Sheet

Ralston 4S Wood-Primer

Ralston
COLOUR & COATINGS



Ralston Colour & Coatings B.V.
Part of Royal Van Wijhe Verf
Russenweg 14
P.O. Box 205
8000 AE Zwolle
Netherlands

T : +31(0)38 - 429 11 00
F : +31(0)38 - 421 04 14

www.ralstoncolour.com
info@ralstoncolour.com

CoC 05063230